



## Magnesium hydroxide suspension for environmental applications MagTreat® — S 65%

## **Description**

Concentrated, stabilized magnesium hydroxide aqueous suspension. Produced from selectively mined natural magnesium hydroxide.

## **Application**

The product is used for acid neutralization, wastewater treatment, heavy metals precipitation, reduction of COD and phosphates, prevention of odor and corrosion in sewage systems, whey neutralization, flue gas desulphurization in power plants and marine scrubber systems (EGCS).

	Parameter	Specification	Typical
	Aqueous Suspension		
	Dry solids, %, min.	60.0	65.0
Properties	Density, kg/m³, min.	1550	1650
	Viscosity, (Brookfield VT, 100 rpm), cps, max.	650	200
	Freezing point, °C	0	0
	On dry solids basis		
	MgO/Mg(OH) <sub>2</sub> , %, min.	62.0/89.9	64.6/93.7
	CaO, %, max.	3.0	2.3
	SiO <sub>2</sub> , %, max.	3.0	1.6
	Fe <sub>2</sub> O <sub>3</sub> , %, max.	0.3	0.12
	*SO₄²-, %, max.	0.01	0.001
	*Cl <sup>-</sup> , %, max.	0.01	0.001
	Specific surface area*, m²/g	9–11	10
	Median particle size $D_{50}$ , microns:		
	Laser diffraction	5.0-6.0	5.5
	Sedimentation technique	2.0-3.0	2.5
	* — is determined once in 6 months		
Equivalents on 100% dry	Na <sub>2</sub> CO <sub>3</sub> (soda ash)	=	1.0 mt equivalent to 0.55 mt $Mg(OH)_2$
	NaOH (caustic soda)	=	1.0 mt equivalent to 0.73 mt $Mg(OH)_2$
solids basis	Ca(OH) <sub>2</sub> (hydrated lime)	=	1.0 mt equivalent to 0.79 mt Mg(OH) <sub>2</sub>
Storage	Shelf life of suspension is 6 months upon arrival at customer's warehouse. For long term storage periodic agitation of the suspension is necessary. Store at the warehouse/vessel with temperature above the freezing point and below the +35 °C avoiding the direct UV exposure. Do not store product in used IBC's.		
Packing	IBC or in bulk.		
Safety	Refers to low-hazard substances; fire- and explosion-proof, non-toxic.		
Transportation	Transported by all modes of transport in accordance with the rules of transportation of goods that operate in this mode of transport. Avoid the long term transportation of the material at the		

temperatures above +35 °C.